

TECHNOMELT PA 6832 BLACK

January 2013

PRODUCT DESCRIPTION

TECHNOMELT PA 6832 BLACK provides the following product characteristics:

Technology	Polyamide
Product Type	Hotmelt
Cure	Physical setting
Condition	thermoplastic
Components	One-component
Application	Molding
Color	Black

TECHNOMELT PA 6832 BLACK provides good adhesion to various substrates, requires only low processing pressure due to the low viscosity, provides an excellent moisture and environmental seal, produces no toxic fumes and provides a good balance of low and high temperature performance. Typical uses include protection for printed circuit boards. This product is typically used in applications with an operating range of -20 °C to 125 °C. This product has a typical molding temperature of 200 °C to 250 °C.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Flash Point - See SDS

Viscosity @ 240°C, mPa·s (cP) 5,700

TYPICAL PROPERTIES OF CURED MATERIAL

Adhesive Properties

Physical Properties:

Density @ 210 °C, g/cm ³	0.98
Elongation, at break, %	300
Glass Transition Temperature, °C	-60
Shore Hardness, ISO 868, Durometer A	92
Shore Hardness, ISO 868, Durometer D	68
Softening Point, DIN EN 1427, °C	153

GENERAL INFORMATION

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage: 8 °C to 21 °C. Storage below 8 °C or greater than 28 °C can adversely affect product properties.

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Conversions

(°C x 1.8) + 32 = °F
kV/mm x 25.4 = V/mil
mm / 25.4 = inches
µm / 25.4 = mil
N x 0.225 = lb
N/mm x 5.71 = lb/in
N/mm² x 145 = psi
MPa x 145 = psi
N·m x 8.851 = lb·in
N·m x 0.738 = lb·ft
N·mm x 0.142 = oz·in
mPa·s = cP

Note

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 0.0

